

LA-UR-20-28625

Approved for public release; distribution is unlimited.

Title:	Single Crystal UO ₂ cube creation using a Xe Plasma FIB
Author(s):	Tegtmeier, Eric Lee Taylor, Caitlin Anne
Intended for:	Inform Foreign National co-investigators of the process involved in making Uranium Oxide cubes that being sent to them for a beam line experiment in Germany.
Issued:	2020-10-26


Disclaimer:

Los Alamos National Laboratory, an affirmative action/equal opportunity employer, is operated by Triad National Security, LLC for the National Nuclear Security Administration of U.S. Department of Energy under contract 89233218CNA000001. By approving this article, the publisher recognizes that the U.S. Government retains nonexclusive, royalty-free license to publish or reproduce the published form of this contribution, or to allow others to do so, for U.S. Government purposes. Los Alamos National Laboratory requests that the publisher identify this article as work performed under the auspices of the U.S. Department of Energy. Los Alamos National Laboratory strongly supports academic freedom and a researcher's right to publish; as an institution, however, the Laboratory does not endorse the viewpoint of a publication or guarantee its technical correctness.





Single Crystal UO_2 cube creation using a Xe Plasma FIB

Eric Tegtmeier Sigma-2
Caitlin Taylor MST-8


Cube from (100) crystal



Top of cube in plan view. Four edges numbered




Four edges of cube prior to lift out







Cube attached to W probe with amorphous carbon (small black splotch at end of needle)


Cube from (111) crystal



Top of cube in plan view. Four sidewalls numbered




Four edges of cube prior to lift out




Cube attached to W probe with amorphous carbon (small black splotch at end of needle)

E beam image of two cubes welded to Cu posts of TEM grid



Optical of two cubes attached to Cu TEM grid
as placed in apiezon grease



Amorphous C deposits are only ~1-2
microns thick at maximum.

